



Joint venture between SGS and IMME Mongolia



SGS IMME MONGOLIA LLC

INSPECTION REPORT

Company : Darkhan Metallurgical Plant
Location: Tumurtei Terminal
Date: 2024.4.6

| Sample No: | Product weight | H ₂ O | Fe | S | Al ₂ O ₃ | SiO ₂ | TiO ₂ | P | Number of Car: | |
|------------------------|----------------|------------------|-------------|--------------|--------------------------------|------------------|------------------|-------------|----------------|-----------|
| | | ton | % | % | % | % | % | % | pcs | |
| TLot 29 | 1 | 671.35 | 2.18 | 58.36 | 0.31 | 2.14 | 6.45 | 0.38 | 0.01 | 10 |
| | 2 | 657.65 | 2.07 | 59.37 | 0.30 | 1.96 | 5.31 | 0.32 | <0.01 | 10 |
| | 3 | 704.30 | 2.06 | 57.86 | 0.30 | 2.15 | 6.37 | 0.33 | <0.01 | 10 |
| | 4 | 710.85 | 2.04 | 60.28 | 0.39 | 1.53 | 4.99 | 0.27 | 0.02 | 10 |
| | 5 | 419.20 | 2.12 | 57.56 | 0.41 | 1.85 | 6.61 | 0.36 | <0.01 | 6 |
| Average result* | | 3,163.35 | 2.09 | 58.78 | 0.34 | 1.93 | 5.89 | 0.33 | 0.01 | 46 |

NOTE: *Average result of all analytes is for summary of product weight.
This result format of the inspection sample only for DMP's internal use only .

Signature



SGS-IMME Mongolia LLC